




RUBBERcomp®

Durable coating
EASY to undress!



RUBBERcomp® LIQUID PAINT

RUBBERcomp® is a multi-purpose, air drying specialty rubber coating. It can be easily applied by spraying. It protects coated items against moisture, acids, abrasion, corrosion, and skidding /slipping, and provides a comfortable, controlled grip.

RUBBERcomp® remains flexible and stretchy over time, and will not crack or become brittle in extreme weather conditions. It has been tested and proven in temperatures from -30°C to +90°C. Easy to peel off. Around four paint layers needed for adequate film thickness.

QUALITY AND PROPERTIES

Base: synthetic rubber polymers
Can be applied wet-on-wet or wet-on-dry
Forms an electric, weather and abrasion proof layer
Remains flexible in wide temperature area
Easy to strip simply by tearing off the rubber layer
Degree of gloss: matt, semi-gloss or high gloss

PHYSICAL AND CHEMICAL DATA

Smell: solvent
Colour: see the label of the can

APPLICATION AREAS

Metal: improved wear resistance, corrosion resistance, vibration reduction, sound damping, electrical insulation
Wood: seals and prevents cracking.
Glass: improves shatter-proof features
Textiles and ropes: weatherproofs, prevents rotting and fraying.
Plastics: forms an elastic, scratch resistant layer.
Rubber: forms an elastic, scratch resistant layer.
Paper and cardboard: provides a weatherproof, tear resistant layer

EU VOC-CONTENT: IIB (e), VOC max. 840g/L (2010), VOC 614g/L

DRYING

Drying time (at 20°C, 50% relative air humidity):
Dust-dry: after 20 minutes
Dry to touch: after 40 minutes

Completely dry: after 10 hours

Final hardness: around 2 days

Recommended applying temperature +18 - +25°C. Applying in cooler temperatures may affect drying times, finish quality, and spray performance.

INSTRUCTIONS FOR USE:

Clean the surface of oils, grease, dirt, wax and loose rust. Dilute 1L paint with 450ml thinner, margin ±5%. Mix well before use. Pneumatic paint guns use compressor pressure 2.5 bar max and nozzle 1.1 - 2.0 mm. Electric paint gun adjustment depending on type. Test always on an external panel first and adjust the spray gun starting from lowest position and increase until you are able to apply a wet, uniform coat without dripping. Spray at least four layers following separate RUBBERcomp® painting instructions / technical information sheet. Do not use any other thinner than RUBBERcomp® thinner.
Before closing the can after use, pour a little thinner on top of the paint to prevent skinning. Do not mix, close the cover.

STORAGE STABILITY:

36 months if appropriate storage provided (=+10°- +25°C, relative air humidity of max. 60%)

SIZES:

250 ml, 1000 ml, 3000ml Liquid
450ml and 800ml Thinner



250 ml



Matt black



Black semigloss



White semigloss



Transparent matt



Transparent high gloss



Smoke semigloss




Neon orange semigloss



Neon green semigloss



Blue semigloss



Red semigloss



Gun metal grey semigloss



Wheel silver high gloss




Neon red semigloss



Yellow semigloss



Camo brown matt



Camo green matt

1 l



Matt black



Black semigloss



White semigloss



Transparent matt



Transparent high gloss



Smoke semigloss



Neon orange semigloss



Neon green semigloss



Blue semigloss



Red semigloss




Gun metal grey semigloss



Wheel silver high gloss




Neon red semigloss



Yellow semigloss



Camo brown matt



Camo green matt



Camo beige matt

3 l




6 412490 028183 CR1921210

Matt black



6 412490 028190 CR1921215

Black semigloss



6 412490 028206 CR1922220

White semigloss



6 412490 028404 CR1923310

Transparent matt



6 412490 028213 CR1923320

Transparent high gloss



6 412490 028220 CR1923350

Smoke semigloss



6 412490 028237 CR1926170

Neon orange semigloss



6 412490 028244 CR1926200

Neon green semigloss



6 412490 028251 CR1928030

Blue semigloss



6 412490 028268 CR1928050

Red semigloss



6 412490 028275 CR1929970

Gun metal grey semigloss



6 412490 028282 CR1929980

Wheel silver high gloss



6 412490 029203 CR1926220

Neon red semigloss



6 412490 028824 CR1928010

Yellow semigloss



6 412490 029197 CR1928160

Camo brown matt



6 412490 029180 CR1928120

Camo green matt



THINNER 800ML

6 412490 028329 CR190100

Thinner 800ml

THINNER 450ML

6 412490 028312 CR190045

Thinner 450ml

